

## SOPRALASTIC 122 HD

### High Performance Roof Coating

**Description:** *SOPRALASTIC 122 HD* is a heavy duty high performance roof coating composed of bitumen, cellulose fibres, mineral fillers and solvent. Mainly used to revitalize existing roofs in order to offer a better protection and to prolong their service life. It may be used on asphalt roofs and metal surfaces.

**Application:** *SOPRALASTIC 122 HD* is easily applied with a brush or with spraying equipment. Repair all cracks and holes before applying *SOPRALASTIC 122 HD*.

*SOPRALASTIC 122 HD* must be applied to a dry, clean, sound surface that is free of dust, rust or oil. If used over an old dry surface, *ELASTOCOL 500* primer is recommended before applying *SOPRALASTIC 122 HD*. The primer must completely dry before *SOPRALASTIC 122 HD* is applied.

When using more than one layer of coating, wait before the first one is completely dry and apply the other coat perpendicular to the previous application.

Apply 2 to 3 L/m<sup>2</sup> (5 to 7.5 US gal/100 ft<sup>2</sup>) depending on surface porosity.

*SOPRALASTIC 122 HD* must be covered by a mineral protection.

### Properties:

Properties	SOPRALASTIC 122 HD
Colour	Black
Solids by weight (%)	80
Specific gravity at 20 °C (kg/L)	1.06
Service temperature range (°C)	up to 85
Application temperature – product (°C)	10 to 35
Application temperature – surface (°C)	-5 to 35
Ultimate elongation (%)	25
Drying time	1 to 8 hours depending on temperature and quantity applied

(All values are nominal)

**Packaging:** 19 L pails  
Shelf life: Up to 12 months in original sealed containers, protected from humidity.

**Cleaning:** Tools can be cleaned with petroleum solvents such as mineral spirits, varsol, xylene, etc.

**Precautions:** *SOPRALASTIC 122 HD* is a flammable product. Store in a cool, dry area above freezing point. Use in a well ventilated area, far from any open flame. Avoid breathing solvent vapours and prolonged skin contact.

**CONSULT THE MATERIAL SAFETY DATE SHEET PRIOR TO USE.**