

SOPRALASTIC 123

Description: **SOPRALASTIC 123** is a black waterproofing coating composed of elastomeric bitumen, mineral fillers and solvents. **SOPRALASTIC 123** is used to revitalize existing roofs in order to offer a better protection and to prolong their service life. It may be used on asphalt roofs and metal surfaces. It must be protected in all cases, either by a coat of **SOPRALASTIC 124 ALU** or small gravel.

Application:

- Carefully clean and dry the surface.
- Cut open and repair blisters.
- If used over an old dry surface, **ELASTOCOL 500** primer is recommended before applying **SOPRALASTIC 123**. Spread **ELASTOCOL 500** (about 0.25 l/m²).
- To repair cracks, spread a first layer of **SOPRALASTIC 123** and cover with a reinforcement fabric strip soaked in **SOPRALASTIC 123** using a trowel.
- Spread **SOPRALASTIC 123** using a brush or a squeegee at 0.5 L/m². Cover **SOPRALASTIC 123** with mineral protection, or a coat of **SOPRALASTIC 124 ALU** at 0.2 to 0.3 L/m².

Properties:

Properties	SOPRALASTIC 123
Specific gravity at 20 °C (kg/l)	1.12
Colour	Black
Solids by weight (%)	72
Resistance to frost	Good
Resistance to UV light	Poor
Drying time	24 hours

(All values are nominal)

Packaging: 19 L pails
Shelf life: Up to 2 years in original sealed containers, in cool and ventilated area.

Cleaning: Tools can be cleaned with petroleum solvents such as mineral spirits, varsol, xylene, etc.

Precautions: **SOPRALASTIC 123 is a highly flammable product.**
Store away from direct sunlight and open flame. Keep ignition sources away during application and until solvent has evaporated. Harmful if inhaled, swallowed or when in contact with skin. In closed areas, ventilate carefully using mechanical means if necessary. Do not pour residues in drains.

CONSULT THE MATERIAL SAFETY DATE SHEET PRIOR TO USE.