

# Bulletin

## Roof Testing Laboratory (ISO 17025)



### Roof System Dynamic Wind Uplift Resistance Results

File number:	MTS-260759
Test date:	2020-07-08
Publication date:	2021-02-22
Last revision date:	N/A
Reappraisal date:	2024-02-22



### MODIFIED BITUMEN ROOF SYSTEM WITH 2-1 SOPRASMART ISO HD AND SOPRATAACK (PARS) PARTIALLY ATTACHED (HYBRIDE) ROOFING SYSTEM

#### Tested Roofing System Summary

Cap sheet membrane:	Modified bitumen membrane / Adhered
Base sheet membrane:	Included to cover board
Cover board:	Board composed of a bitumen membrane over a polyisocyanurate board 3 x 8 ft x ½ in / Adhered
Upper insulation:	Polyisocyanurate foam insulation board 4 x 4 ft x 1½ in / Adhered
Bottom insulation:	Polyisocyanurate foam insulation board 4 x 4 ft x 2 in / Mechanically fastened
Vapour barrier:	Self-adhesive membrane
Thermal barrier:	Optional
Decking:	Steel deck

#### Dynamic Uplift Resistance (DUR) as per CSA A123.21

System Designation	Measured Value	Computed Value (To Include 1.5 Experimental Factor)
A	-7,2 kPa (-150 psf)	-4,8 kPa (-100 psf)

According to the scope of accreditation published on the SCC website  
Accredited Laboratory No. 797



# Roof Testing Laboratory (ISO 17025)



## Roof System Dynamic Wind Uplift Resistance Results

MTS-260759

### Products

CAP SHEET MEMBRANE				
TESTED PRODUCT: Membrane composed of SBS modified bitumen and a composite reinforcement, the surface is protected by granules and the underside is sanded.				
System	Application Method			
A	Fully adhered with SOPRATAACK (application rate of 27,1 ft <sup>2</sup> /gal or 1,5 L/m <sup>2</sup> )			
ELIGIBLE PRODUCT(S)				
SOPREMA	COLPLY TRAFFIC CAP	SOPRALENE 180 FR GR	SOPRASTAR GR	SOPRASTAR FR GR
	COLPLY TRAFFIC CAP FR	COLPLY TRAFFIC CAP FLEX	SOPRASTAR GR FLEX	COLPLY TRAFFIC CAP FR FLEX
	SOPRASTAR GR FR FLEX	SOPRALENE 250 GR		
SOPREMA System with gravel surfacing	COLPLY BASE 410 FLEX	ELASTOPHENE SANDED	ELASTOPHENE 180 SANDED	SOPRALENE 180 SANDED
	COLPLY BASE 410			
Note: Follow the manufacturer's recommendations for the definition of the type of gravel / amount of gravel / adhesive rate in which to embed the gravel.				

BASE SHEET MEMBRANE
TESTED PRODUCT: Included to cover board

COVER BOARD			
TESTED PRODUCT: Base sheet panel composed of SBS modified bitumen membrane with of a non-woven polyester reinforcement, factory-laminated on a high density polyisocyanurate insulation support panel.			
System	Application Method		Fastening Rate
A	Adhered		Full spread (27,8 ft <sup>2</sup> /gal or 1,5 L/m <sup>2</sup> )
ELIGIBLE THICKNESS(ES)			
½ in			
FASTENING METHOD			
SOPRATAACK Adhesive			
ELIGIBLE PRODUCT(S)			
SOPREMA	2-1 SOPRASMART ISO HD SANDED	2-1 SOPRASMART BOARD SANDED	

# Roof Testing Laboratory (ISO 17025)



## Roof System Dynamic Wind Uplift Resistance Results

MTS-260759

INSULATION (Top Row)				
TESTED PRODUCT: Polyisocyanurate foam insulation board laminated on both sides with fiber reinforced organic felt.				
System	Application Method		Fastening Rate	
A	Adhered		Full spread (27,8 ft <sup>2</sup> /gal or 1,5 L/m <sup>2</sup> )	
ELIGIBLE THICKNESS(ES)				
1½ to 4 in				
FASTENING METHOD				
SOPRATAACK Adhesive				
ELIGIBLE PRODUCT(S)				
SOPREMA	SOPRA-ISO	SOPRA-ISO PLUS		
Atlas Roofing Corp.	ACFoam-II	ACFoam-III	ACFoam-IV	
Johns Manville	ENRGY 3	ENRGY 3 CGF		
Hunter Panels	H-Shield	H-Shield CG		

# Roof Testing Laboratory (ISO 17025)



## Roof System Dynamic Wind Uplift Resistance Results

MTS-260759

INSULATION (Bottom Row)				
TESTED PRODUCT: Polyisocyanurate foam insulation board laminated on both sides with fiber reinforced organic felt.				
System	Application Method		Fastening Rate	
A	Mechanically fastened		8 fasteners per 4 x 4 ft board	
ELIGIBLE THICKNESS(ES)				
2 to 4 in				
FASTENING METHOD				
Screws and plates				
FASTENING PATTERN				
ELIGIBLE PRODUCT(S)				
<b>SOPREMA</b>	SOPRA-ISO	SOPRA-ISO PLUS		
<b>Atlas Roofing Corp.</b>	ACFoam-II	ACFoam-III	ACFoam-IV	
<b>Johns Manville</b>	ENRGY 3	ENRGY 3 CGF		
<b>Hunter Panels</b>	H-Shield	H-Shield CG		



VAPOUR BARRIER				
TESTED PRODUCT: Self-adhesive membrane composed of a trilaminated woven polyethylene and SBS modified bitumen.				
System	Fastening Method		Primer	
A	Self-adhered		N/A	
ELIGIBLE PRODUCT(S)				
SOPREMA	SOPRAVAP'R			
	SOPRAPLY STICK DUO			
Note: thermal barrier required on steel deck.				
SOPREMA	SOPRALENE 180 SP 3.5	ELASTOPHENE SP 2.2		
	Note: thermal barrier required on steel deck or wood deck.			
SOPREMA	SOPRAVAP'R	SOPRALENE STICK	SOPRAPLY STICK DUO	
	Note: on wood deck primed according to the manufacturer's recommendations.			
SOPREMA	ELASTOPHENE SANDED	ELASTOPHENE 180 SANDED	SOPRALENE 180 SANDED	COLPLY BASE 410
	Note: thermal barrier required on steel deck.			

THERMAL BARRIER				
TESTED PRODUCT : Optional				
ELIGIBLE PRODUCT(S)				
CGC	Securock (½ in min.)			
Unifix	PermaBase Dek (½ in min.)			
Application method: loose laid, adhered or mechanically fastened, the fastening method and rate are under the responsibility of the designer.				



<b>FASTENERS</b>		
TESTED PRODUCT(S): #12 roofing fasteners.		
<b>System</b>	<b>Screws</b>	<b>Plates</b>
<b>A</b>	#12 DP 2 $\frac{3}{8}$ in	3 in insulation metal plates
<b>FASTENERS MEASURED PULL OUT RESISTANCE</b>		
427 lbf		
<b>ELIGIBLE PRODUCT(S)</b>		
<b>SOPREMA</b>	#12 DP 2 $\frac{3}{8}$ in	3 in insulation metal plates

<b>ADHESIVE</b>			
TESTED PRODUCT: Two-component polyurethane adhesive.			
<b>System</b>	<b>Ribbon's spacing</b>		<b>Primer</b>
<b>A</b>	Full spread		N/A
<b>ELIGIBLE PRODUCT(S)</b>			
<b>SOPREMA</b>	SOPRATAACK	SOPRATAACK WINTER	COLPLY EF



### General Notes

#### 1. Decking:

The tests performed by EXP Services inc. « EXP » were performed over a standard roll formed steel deck profile, with a galvanized or aluminum / zinc alloy coating finished, as per ASTM A653, A792, A1008 or CSSBI 10M standards, bearing a thickness of 0.76 mm (0.03 inch) minimum (commonly defined as 22 gauge), corresponding to the ASTM A653M grade SS 230, having a yield point of 230 MPa (33 ksi) and a tensile strength of 310 MPa (45 Ksi). Tests could be performed on concrete deck or standard 4' x 8' x 5/8" plywood deck to assess eligibility for possible equivalencies.

The deck's fastening to the supporting structure must be strong enough to resist wind uplift loads (as defined per NBC requirements).

#### 2. Deck equivalency products:

18 to 22 gage steel deck. Wood or concrete deck which testing gave equivalent or superior uplift resistance than the value specified in the "Fasteners Pull Out Resistance" section.

#### 3. Fasteners Pull Out Resistance:

Testing were conducted in laboratory according to ANSI/SPRI FX-1 2011 standard, over a minimum of 10 test samples on a **Com-Ten** apparatus over steel deck (unless stated otherwise).

#### 4. Adhesive Pull Resistance:

Testing were conducted in laboratory over 3 test samples, according to ANSI/SPRI IA-1 2010 standard on a **Com-Ten** apparatus over steel deck (unless stated otherwise) or, according to ASTM D1623 standard over a universal press testing bench, for in-between materials.

#### 5. Note on adhesive:

It is EXP opinion that the application of the adhesive beads in an "S" or straight-line arrangement will not affect the results of this publication. The intention at the job site should be that the glue bead spacings be reasonably distributed on the substrate, in order to come as close as possible to the theoretical patterns when the boards are laid in. Comply with all additional manufacturer's requirements regarding the use of adhesives.

#### 6. Equivalent products:

Only the products listed in this report under eligible products are deemed acceptable as substitute to the tested products. Any other modifications must be requested in written, on EXP application form, to be studied for approval.

#### 7. Optional components:

Any components of this roofing system listed as optional, may be removed from the roof design. Inclusion or exclusion of the said component having no effect on the published dynamic uplift resistance results. (DUR).

#### 8. Experimental factor:

In accordance with CSA A123.21 standard, the published dynamic uplift resistance (DUR) include a computed experimental factor of 1,5.

# Roof Testing Laboratory (ISO 17025)



## Roof System Dynamic Wind Uplift Resistance Results

MTS-260759

### 9. Building Wind Load Calculation:

An online calculator is available at <https://www.nrc-cnrc.gc.ca>.

The calculator will compute, the Wind Load of any given building, for field, perimeter and corners, as per 2015 CNB requirement, without experimental factor. It will also compute perimeter's and corner's zone dimensions.

### 10. Technical Advisories:

This roof system assessment reports must be read in conjunction with any issued technical advisories from EXP.

### 11. Notice:

EXP reserves the right to withdraw, without prior notice, any Bulletin of Roof System Dynamic Wind Uplift Resistance Results published and/or make any necessary corrections.

The information in this roofing system report (the "Report") are based on the tests run by EXP of certain combination of materials in a specific and controlled condition to determine the resistance of different roofing systems to wind uplift forces (the "Test"). The results of the Test are subject to certain prerequisite conditions and assumptions made during the Test. In this regard, the Report is for the exclusive use of EXP client for whom the Report was prepared. The information contained in the Report must not be reproduced, used or relied upon in whole or in part without the written consent of EXP. Any third-party user assumes sole responsibility for the use it makes of the information in the Report including but not limited to any decision to purchase roofing material in reliance of the information found in the Report or on the Site. **Exp disclaims all warranties as to the accuracy, completeness or adequacy of the information in the Report or on the Site and accepts no responsibility for damages suffered by any third party arising out of decisions made or actions based on the Report.**

### 12. Version tracking table:

2021-02-22	First edition.

Prepared by:

EXP Services Inc.

---

Serge Rochon, P. Eng.  
O.I.Q. N° : 114865  
P.E.O. N° : 100023274  
Provincial Manager – Building science and CSA laboratory

---

2021-02-22  
Date