

# Bulletin

## Roof Testing Laboratory (ISO 17025)

UL Third Party Test Data Program participant



## Roof System Dynamic Wind Uplift Resistance Results

File number:	MTS-21009986
Test date:	2021-06-11
Reappraisal date:	2024-09-28



### COLPLY TRAFFIC CAP / COLPLY BASE 410 OVER SOPRA-ISO PLUS HD 1/2" (PARS) PARTIALLY ATTACHED (HYBRID) ROOFING SYSTEM

#### Tested Roofing System Summary

Cap sheet membrane:	Modified bitumen membrane / Adhered
Base sheet membrane:	Modified bitumen membrane / Adhered
Cover board:	High-density polyisocyanurate cover board 4 x 8 ft x 1/2 in / Mechanically fastened
Insulation:	Polyisocyanurate foam insulation board 4 x 8 ft x 1 1/2 in / Loose laid
Vapour barrier:	Self-adhesive membrane
Thermal barrier:	Optional
Decking:	Steel deck

#### Dynamic Uplift Resistance (DUR) as per CSA A123.21

System Designation	Measured testing value According to CSA A123.21:20	Result reduced by a factor of 1,5 According to CSA A123.21:14
A	-4,8 kPa (-100 psf)	-3,2 kPa (-67 psf)

According to the scope of accreditation published on the SCC website  
Accredited Laboratory No. 797





### Products

CAP SHEET MEMBRANE				
TESTED PRODUCT: Membrane composed of SBS modified bitumen and a composite reinforcement, the surface is protected by granules and the underside is sanded.				
System	Application Method			
A	Fully adhered with SOPRATAACK. Application rate between 29,5 and 48,9 ft <sup>2</sup> /gal (0,85 and 1,40 L/m <sup>2</sup> ) depending on substrate. Follow additional manufacturer's instructions.			
ELIGIBLE PRODUCT(S)				
SOPREMA	COLPLY TRAFFIC CAP	SOPRALENE 180 FR GR	SOPRASTAR GR	SOPRASTAR FR GR
	COLPLY TRAFFIC CAP FR	SOPRALENE 250 GR	SOPRALENE 180 GR	COLPLY TRAFFIC CAP FLEX
	COLPLY TRAFFIC CAP FR FLEX	SOPRASTAR GR FLEX	SOPRASTAR GR FR FLEX	
SOPREMA System with gravel surfacing	COLPLY BASE 410 FLEX	ELASTOPHENE SANDED	ELASTOPHENE 180 SANDED	SOPRALENE 180 SANDED
	COLPLY BASE 410			
Note: Follow the manufacturer's recommendations for the definition of the type of gravel / amount of gravel / adhesive rate in which to embed the gravel.				

BASE SHEET MEMBRANE				
TESTED PRODUCT: Membrane composed of SBS modified bitumen and a composite reinforcement, sanded on both sides.				
System	Application Method			
a	Fully adhered with SOPRATAACK. Application rate between 29,5 and 48,9 ft <sup>2</sup> /gal (0,85 and 1,40 L/m <sup>2</sup> ) depending on substrate. Follow additional manufacturer's instructions.			
ELIGIBLE PRODUCT(S)				
SOPREMA	COLPLY BASE 410	ELASTOPHENE SANDED	ELASTOPHENE 180 SANDED	SOPRALENE 180 SANDED
	COLPLY BASE 410 FLEX			



COVER BOARD				
TESTED PRODUCT: High-density polyisocyanurate cover board composed of a closed-cell core structure placed between two polymers coated glass fibers facers.				
System	Application Method	Fastening Rate		
A	Mechanically fastened	18 fasteners / 4 x 8 ft board		
ELIGIBLE THICKNESS(ES)				
½ in minimum				
FASTENING METHOD				
Screws and plates				
FASTENING PATTERN				
ELIGIBLE PRODUCT(S)				
<b>SOPREMA</b>	SOPRA-ISO PLUS HD			

# Roof Testing Laboratory (ISO 17025)



## Roof System Dynamic Wind Uplift Resistance Results

MTS-21009986

INSULATION				
TESTED PRODUCT: Polyisocyanurate foam insulation board laminated on both sides with fiber reinforced organic felt.				
System	Application Method			Fastening Rate
A	Loose laid			n/a
ELIGIBLE THICKNESS(ES)				
1½ in minimum				
ELIGIBLE PRODUCT(S)				
SOPREMA	SOPRA-ISO	SOPRA-ISO PLUS	SOPRAROCK DD	SOPRAROCK DD PLUS
Atlas Roofing Corp.	ACFoam-II	ACFoam-III	ACFoam-IV	
Johns Manville	ENRGY 3	ENRGY 3 CGF		
Hunter Panels	H-Shield	H-Shield CG		

ADDITIONAL INSULATION				
TESTED PRODUCT: Optional (any thickness from any eligible insulation products listed above).				

VAPOUR BARRIER				
TESTED PRODUCT: Self-adhesive membrane composed of a trilaminated woven polyethylene and SBS modified bitumen.				
System	Fastening Method			Primer
A	Self-adhered			n/a
ELIGIBLE PRODUCT(S)				
SOPREMA	SOPRAVAP'R			
SOPREMA	SOPRAPLY STICK DUO			
	Note: thermal barrier required on steel deck.			
SOPREMA	SOPRALENE 180 SP 3.5	ELASTOPHENE SP 2.2		
	Note: thermal barrier required on steel deck or wood deck.			
SOPREMA	SOPRAVAP'R	SOPRALENE STICK	SOPRAPLY STICK DUO	
	Note: on wood deck primed according to the manufacturer's recommendations.			

# Roof Testing Laboratory (ISO 17025)



## Roof System Dynamic Wind Uplift Resistance Results

MTS-21009986

THERMAL BARRIER				
TESTED PRODUCT : Optional.				
ELIGIBLE PRODUCT(S)				
<b>Georgia-Pacific</b>	DensDeck (½ in min.)	DensDeck Prime (½ in min.)		
<b>CGC</b>	Securock (½ in min.)			
<b>Unifix</b>	PermaBase Dek (½ in min.)			
Application method: loose laid, adhered or mechanically fastened, the fastening method and rate are under the responsibility of the designer.				

FASTENERS (see general note #3)		
TESTED PRODUCT(S): #12 roofing fasteners.		
System	Screws	Plates
<b>A</b>	#12 DP	3 in round metal plates
FASTENERS MEASURED PULL OUT RESISTANCE		
369 lbf (measured)		
ELIGIBLE PRODUCT(S)		
<b>SOPREMA</b>	Dekfast #12 DP	3 in round metal plates

ADHESIVE			
TESTED PRODUCT: Two-component polyurethane adhesive.			
System	Ribbon's spacing		Primer
<b>A</b>	Full spread		n/a
ELIGIBLE PRODUCT(S)			
<b>SOPREMA</b>	SOPRATAACK	SOPRATAACK WINTER	COLPLY EF
	Respect the adhesive rates prescribed by the manufacturer.		

# Roof Testing Laboratory (ISO 17025)



## Roof System Dynamic Wind Uplift Resistance Results

MTS-21009986

DECKING					
PRODUCT: Steel deck.					
Grade	Thickness (in)	Yield strength (ksi)	Tensile strenght	Span spacing (in)	Fasteners spacing (in)
230	0,03	33	45 ksi	54	6

Additional testing could be performed on concrete decks or standard 4' x 8' x 5/8" plywood decks to assess eligibility for possible equivalencies. On a building, the attachment of the decking to the supporting structure must be strong enough to resist wind uplift loads (as defined per NBCC requirements).

# Roof Testing Laboratory (ISO 17025)



## Roof System Dynamic Wind Uplift Resistance Results

MTS-21009986

### General Notes

**1. Source:**

This publication is based on a test conducted by **EXP Services inc.**

**2. Deck equivalency products:**

18 to 22 gage steel deck. Wood or concrete deck which testing gave equivalent or superior uplift resistance than the value specified in the "Fasteners Pull Out Resistance" section.

**3. Fasteners Pull Out Resistance:**

Tests were conducted in laboratory according to ANSI/SPRI FX-1 2011 standard, over a minimum of 10 test samples on a **Com-Ten** apparatus over steel deck (unless stated otherwise).

**4. Adhesive Pull Resistance (when applicable):**

Tests were conducted in laboratory over 3 test samples, according to ANSI/SPRI IA-1 2010 standard on a **Com-Ten** apparatus over steel deck (unless stated otherwise) or, according to ASTM D1623 standard over a universal press testing bench, for in-between materials.

**5. Note on adhesive:**

It is EXP opinion that the application of the adhesive beads in an "S" or straight-line arrangement will not affect the results of this publication. The intention at the job site should be that the glue bead spacings be reasonably distributed on the substrate, in order to come as close as possible to the theoretical patterns when the boards are laid in. Comply with all additional manufacturer's requirements regarding the use of adhesives.

**6. Liquid primers and adhesives:**

Please observe the application rates specified by the manufacturers, as well as any additional requirements when applying liquid primers and adhesives.

**7. Equivalent products:**

Only the products listed in this report under eligible products are deemed acceptable as substitute to the tested products. Any other modifications must be requested in written, on EXP application form, to be studied for approval.

**8. Optional components:**

Any components of this roofing system listed as optional, may be removed from the roof design. Inclusion or exclusion of the said component having no effect on the published dynamic uplift resistance results. (DUR).

**9. Experimental factor:**

In accordance with CSA A123.21 -14 standard, the published dynamic uplift resistance (DUR) includes a computed experimental factor of 1,5.

# Roof Testing Laboratory (ISO 17025)



## Roof System Dynamic Wind Uplift Resistance Results

MTS-21009986

### 10. Building Wind Load Calculation:

An online calculator is available at <https://www.nrc-cnrc.gc.ca>.

The calculator will compute, the Wind Load of any given building, for field, perimeters and corners, as per 2015 NBCC requirement, without experimental factor. It will also compute perimeters' and corner's zone dimensions.

### 11. Technical Advisories:

This roof system assessment reports must be read in conjunction with any issued technical advisories from EXP.

### 12. Notice:

EXP reserves the right to withdraw, without prior notice, any Bulletin of Roof System Dynamic Wind Uplift Resistance Results published and/or make any necessary corrections.

The information in this roofing system report (the "Report") are based on the tests run by EXP of certain combination of materials in a specific and controlled condition to determine the resistance of different roofing systems to wind uplift forces (the "Test"). The results of the Test are subject to certain prerequisite conditions and assumptions made during the Test. In this regard, the Report is for the exclusive use of EXP client for whom the Report was prepared. The information contained in the Report must not be reproduced, used or relied upon in whole or in part without the written consent of EXP. Any third-party user assumes sole responsibility for the use it makes of the information in the Report including but not limited to any decision to purchase roofing material in reliance of the information found in the Report or on the Site. **Exp disclaims all warranties as to the accuracy, completeness, or adequacy of the information in the Report or on the Site and accepts no responsibility for damages suffered by any third party arising out of decisions made or actions based on the Report.**

### 13. Version tracking table:

2021-09-28	First edition.

Prepared by:

EXP Services Inc.

---

Serge Rochon, P. Eng.  
O.I.Q. N° : 114865  
P.E.O. N° : 100023274  
Provincial Manager – Building science and CSA laboratory

---

2021-09-28  
Date